

		<p>9420 Santa Anita Avenue Rancho Cucamonga, CA 91730-6117 (909) 987-0550 (800) 538-3091 Fax: (909) 987-0490 http://www.supergluecorp.com</p>
PRODUCT DATA SHEET		Permanent Thread Lock

Pacer Technology Permanent Thread Lock is formulated for use in locking, sealing, joining, and fastening of threaded metal components. Permanent Thread Lock fills gaps to 0.01". Resistant to oil, gasoline, solvents and automotive fluids, Permanent Thread Lock resists temperatures to 300°F (149°C).

PROPERTIES

Liquid State

Chemical Base

Color	Permanent Thread Lock
Specific Gravity (25 ⁰ F/4 ⁰ C)	Anaerobic compound
Flashpoint COC ⁰ F (⁰ C)	Red Liquid
Viscosity, cP	1.1
Typical Gap (Inches)	>200 (>93)
Fixture Time, minutes	200-800
Working Time, hours	.008
Full Cure, hours	<25
Corrosivity: MIL-S-22473D	2
Toxicity	24
Soluble In:	none
	low
	Acetone, MEK, Nitromethane

Cured State

Service Temperature Range	-60 ⁰ F to +300 ⁰ F (-51 ⁰ C to +149 ⁰ C)
Locking Torque*	
(in-lbs) Breakaway	130-330
Prevailing	190-450
Shore D Hardness	>70
Soluble In:	Pacer X-8 Debonder, Acetone, Nitromethane

* Breakaway & prevailing torque tested on 3/8 zinc nuts and bolts.

STORAGE AND SHELF LIFE

For optimum results, store below 90°F (32°C) in original containers. Stored under these conditions, a one year shelf life can be expected.

APPLICATION AND CURE CHARACTERISTICS

For best results, parts should be clean and free from oil and grease, or other contaminants. Recommended surface finish is 30-80 inches. Smoother surfaces will result in lower bond strength, rougher surfaces may provide excess gap.

Fixture and cure speed is dependent upon surface activity of the metal being utilized. Steel, brass, copper, iron, and aluminum alloys containing copper will fixture faster than plated surfaces, stainless steel, and pure aluminum. Primer can be used to speed up cure. Product can be fully cured at 200⁰ F (93⁰ C) for 30 minutes or at 250⁰ F (121⁰ C) for 25 minutes.

Apply a bead around part to be bonded and assemble with a twisting motion to spread adhesive. Liquid adhesive will not center the part automatically, and additional fixture is recommended until adhesive reaches handling strength. Excess adhesive on the outside of the joint will not cure, and can be removed with a solvent-soaked cloth.

SAFETY AND HANDLING PRECAUTIONS:

Liquid adhesive can irritate skin and eyes. Vapor In case of eye contact, flush with water for 15 minutes, see a physician if symptoms persist. If swallowed, do not induce vomiting. Get immediate medical attention. Use of safety glasses, protective clothing and gloves recommended for prolonged exposure to liquid adhesive.

For more information, refer to Material Safety Data Sheet, available upon request. In case of emergency, call Pacer Technology at 800-538-3091 (outside CA only), or 909-987-0550.

PRODUCT NUMBER: N27106, N27150

01/02mkr

The data contained herein is furnished for descriptive purposes only and is believed to be reliable. Users of any products described in the data sheet have the responsibility to determine the suitability for their particular use thereof, and Pacer relies upon such users to adopt all necessary precautions to ensure the protection of property and persons against hazards involved in the use thereof.

Pacer Technology specifically makes no warranty, representation, or condition of any nature, kind or character, whether express or implied, including, but not limited to, warranties or merchantability or fitness for a particular purpose arising from the sales or use of products described in this data sheet, and none shall be implied by law. Pacer Technology specifically disclaims any liability for consequential or incidental damage of any kind, including lost profit.